



Certificate of Antibacterial Analysis

CERTIFICATE NO.	BC026/2018	DATE RECEIVED	06.03.18
CUSTOMER	GRATNELLS LTD	DATE ANALYSED	20.03.18
CUSTOMER REF.	180/142	DATE REPORTED	23.03.18

UNITS OF RESULTS	Colony Forming Units/CM ²	NO. OF PAGES	1 of 1
-------------------------	--------------------------------------	---------------------	--------

Method of Analysis: Determination of Antibacterial Activity using ISO 22196: 2011

Sample	Test Organism	Contact Time		Reduction (Initial)	
		0 hrs	24 hrs	Log ₁₀	%
501 METAL LID FOR TROLLEY, POWDER COATED STEEL WITH BIOCOTE	MRSA	1.17E+05	2.80E+03	1.62	97.60%
501 METAL LID FOR TROLLEY, POWDER COATED STEEL WITH BIOCOTE	<i>E.coli</i>	1.91E+05	3.47E+03	1.74	98.18%

The above data describe the difference in the population sizes of the test organisms, relative to the initial (0 hours) population, following contact with the surface of the samples detailed in this CoA for 24 hours at 35°C under a RH of >95%. These conditions are those specified by the ISO 22196: 2011 method of analysis.

Comment: The sample 501 METAL LID FOR TROLLEY, POWDER COATED STEEL WITH BIOCOTE has achieved the BioCote minimum antibacterial performance requirement of 95% "Reduction against the Initial for *E.coli* and MRSA" according to ISO 22196: 2011 analysis.

FOR BIOCOTE LTD

Technical Manager
Megan Hughes

PROVEN ANTIMICROBIAL PROTECTION

